



Certificate of Analysis 0991

Date: 11-17-2023

Version: 01

CRM ITAK-119

Certified Reference Material – Iron ore

Table 1 – ITAK-119 – Certified Values

Element/Unit	Certified Value ^[1]	s ^[2]	s _r ^[3]	s _L ^[4]	U ^[5]
Fe (%) ^{a, d}	63.75	0.14	0.087	0.11	± 0.028
Al ₂ O ₃ (%) ^{a, b, e}	2.302	0.038	0.025	0.029	± 0.0083
SiO ₂ (%) ^{a, b, e, f}	1.278	0.039	0.028	0.027	± 0.0077
Mn (%) ^{a, b, e}	0.0739	0.0021	0.0016	0.0013	± 0.00038
TiO ₂ (%) ^{a, b, e}	0.0652	0.0063	0.0026	0.0058	± 0.0014
P (%) ^{a, b, e}	0.0503	0.0018	0.0010	0.0015	± 0.00040
CaO (%) ^{a, b}	0.0108	0.0042	0.0011	0.0041	± 0.0014
MgO (%) ^{a, b, e}	0.1069	0.0064	0.0036	0.0053	± 0.0017
FeO (%) ^d	0.88	0.13	0.015	0.13	± 0.047
^[6] LOI (%) ^c	5.05	0.12	0.038	0.12	± 0.029

^[1] The Certified Value was calculated according to ISO Guide 35 and ISO 5725-2.

^[2] The standard deviation for proficiency assessment was calculated according to ISO 13528 and 5725-2. This standard deviation can be used for control charts for individual analysis ($n=1$).

^[3] The within-laboratory standard deviation was calculated according to ISO 5725-2.

^[4] The between-laboratory standard deviation was calculated according to ISO 5725-2.

^[5] The extended standard uncertainty of the mean ($\alpha=5\%$) was calculated according to ISO Guide 35.

^[6] Loss On Ignition.

Note: The letters in front of the elements are codes for Analytical Methods used.

Table 2 – ITAK-119 – Informative Values

Element/Unit	Reference Value ^[7]
Na ₂ O (%) ^{a, e}	< 0.02
K ₂ O (%) ^a	< 0.01

^[7] These values are informative. They were calculated according to ISO Guide 35 and ISO 5725-2 from thirty to thirty-five results from a varying number of laboratories.

DESCRIPTION

ITAK-119 was prepared from a sample of Iron ore donated by an Iron ore Mining Company from the Southeast of Brazil in 2023.

This Certified Reference Material (CRM) is presented as a fine powder.

INTENDED USE AND INSTRUCTIONS

ITAK-119 provides an important control in analytical data from exploration and can be used as a tool for grade control in routine mining and laboratory operations.

This Certified Reference Material can be used for calibration of analytical equipment, assess and develop new methods, validation of analytical methods, and arbitration – proficiency testing for example.

The bottles/sachets content should be thoroughly mixed before taking samples of ITAK-119.

The Certified Reference Material should be used without pre-treatment. ITAK is not responsible for any changes occurring after opening said bottles/sachets.

The Certified Reference Material should be stored in a dry place and without contact with excessive heat or moisture.

CERTIFICATION AND STATISTICAL EVALUATION OF ANALYTICAL DATA

ITAK-119 was analyzed by twenty-three specialized laboratories. The statistical evaluation was carried out according to ISO GUIDE 35 and ISO 5725-2, using: identification and treatment of outliers, stragglers and technically invalid data, certified value calculation, standard deviation calculation, and extended standard uncertainty calculation.

The Technical Report: RT-040/2023 STD contains full details of all phases of manufacturing, certifying results, participating laboratories, and the statistical evaluation.

Note: This report is available on the ITAK database for CRM users.

ANALYTICAL METHODS

The methods used on the certification of CRM ITAK-119 are mentioned as follows:

- a: Fusion method and determination by X-Ray Fluorescence.
- b: Fusion method and determination by Atomic Emission Spectrometry (ICP).
- c: Gravimetric method.
- d: Acid digestion method and determination by Titrimetric method.
- e: Acid digestion method and determination by Atomic Emission Spectrometry (ICP).
- f: Acid digestion method and determination by Gravimetry.

PERIOD OF VALIDITY

This CRM certification is valid until: **November 17, 2033.**

CERTIFICATE REPRODUCTION

This certificate must not be modified and may only be reproduced in its entirety and without change.



Bráulio de Freitas Pessoa
Chemist – CRQ 02.202.008
Technical Director