Certificate of Analysis 1065

Issue Date: 05-19-2025 Version: 01

CRM ITAK-1103 Certified Reference Material – Lithium Ore Table 1 – ITAK-1103 – Certified Values

ITAK

Element/Unit	Certified Value ^[1]	s ^[2]	S r ^[3]	S _L ^[4]	U [5]
Al (%) ª	8.41	0.16	0.086	0.13	± 0.052
Be (g/t) ^{a, b}	147.8	3.1	2.5	1.8	± 0.96
Ca (%) ^{a, b}	0.489	0.044	0.035	0.026	± 0.012
Cr (g/t) ^{a, b}	369	43	35	25	± 10
Fe (%) ^{a, b}	0.676	0.015	0.013	0.0088	± 0.0040
K (%) ^{a, b}	1.920	0.063	0.040	0.048	± 0.019
Li (%) ^{a, b}	0.3857	0.0088	0.0048	0.0074	± 0.0029
Mn (%) ^{a, b}	0.0981	0.0035	0.0026	0.0023	± 0.0010
Nb (g/t) ^{a, b}	27.9	4.7	2.7	3.8	± 1.8
Si (%) ª	36.06	0.71	0.27	0.65	± 0.33
Sn (g/t) ^{a, b}	54.6	7.0	2.6	6.5	± 2.9
Ta (g/t) ^{a, b}	20.1	1.8	1.8	0.0085	± 0.38
Ti (%) ^{a, b}	0.0335	0.0026	0.00054	0.0026	± 0.0010
Zn (g/t) ^{a, b}	204.3	9.6	6.4	7.2	± 3.2

^[1]The Certified Value was calculated according to ISO Guide 35 and ISO 5725-2. ^[2] The standard deviation for proficiency assessment was calculated according to ISO 13528 and 5725-2. This standard deviation can be used for control charts for individual analysis (n=1).

^[3] The within-laboratory standard deviation was calculated according to ISO 5725-2.

^[4] The between-laboratory standard deviation was calculated according to ISO 5725-2.

^[5] The extended standard uncertainty of the mean (α =5%) was calculated according to ISO Guide 35.

Note: The letters in front of the elements are codes for the Analytical Methods used.



Table 2 – ITAK-1103 – Informative Values

Element/Unit	Reference Value ^[6]		
P (%) ª	0.110		

^[6] These values are informative. They were calculated according to ISO Guide 35 and ISO 5725-2 from fifteen results, from various laboratories.

DESCRIPTION

ITAK-1103 was prepared from a sample of Lithium Ore donated by a Lithium Ore Project from Southeast Brazil in 2025.

This Certified Reference Material (CRM) is presented as a fine powder.

INTENDED USE AND INSTRUCTIONS

ITAK-1103 provides important control in analytical data from exploration and can be used as a tool for grade control in routine mining and laboratory operations.

This Certified Reference Material can be used, for example, to calibrate analytical equipment, assess and develop new methods, validate analytical techniques, and arbitrate proficiency testing.

The bottles/sachets' content should be thoroughly mixed before taking samples of ITAK-1103.

The Certified Reference Material should be used without pre-treatment. ITAK is not responsible for any changes after opening the bottles/sachets.

The Certified Reference Material should be stored in a dry place and without contact with excessive heat or moisture.

The minimum test portion of the Certified Reference Material is 0.5 g.

CHARACTERISATION AND STATISTICAL EVALUATION OF ANALYTICAL DATA

Nine specialised laboratories analysed ITAK-1103. The statistical evaluation was carried out according to ISO GUIDE 35 and ISO 5725-2, using: identification and treatment of outliers, stragglers and technically invalid data, certified value calculation, standard deviation calculation, and extended standard uncertainty calculation.

The certified values are metrologically traceable to the International System of Units (SI) derived unit for mass fraction (expressed as percent).



The Technical Report RT-013/2025 STD contains full details of all manufacturing phases, certifying results, participating laboratories, and the statistical evaluation. <u>Note</u>: This report is available for CRM users on the ITAK database.

ANALYTICAL METHODS

The methods used in the characterisation of CRM ITAK-1103 are mentioned as follows:

- a: Sodium peroxide Fusion Method and Atomic Emission Spectrometry (ICP-OES) determination.
- **b**: Sodium peroxide Fusion Method and Atomic Emission Spectrometry (ICP-MS) determination.

PERIOD OF VALIDITY

This CRM certification is valid until May 19, 2035.

CERTIFICATE REPRODUCTION

This certificate must not be modified and may only be reproduced in its entirety and without change.

Olesson

Bráulio de Freitas Pessoa Chemist – CRQ 02.202.008 Technical Director